



Mirafi[®] 550X

Mirafi[®] 550X geotextile is composed of high-tenacity polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. Mirafi[®] 550X geotextile is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Typical Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D 4595	kN/m (lbs/in)	29.8 (170)	29.8 (170)
Grab Tensile Strength	ASTM D 4632	kN (lbs)	1.5 (340)	1.3 (285)
Grab Tensile Elongation	ASTM D 4632	%	25	17
Trapezoid Tear Strength	ASTM D 4533	kN (lbs)	0.5 (120)	0.5 (120)
Mullen Burst Strength	ASTM D 3786	kPa (psi)	4545 (660)	
Puncture Strength ¹	ASTM D 4833	kN (lbs)	0.7 (150)	
CBR Puncture Strength	ASTM D 6241	kN (lbs)	4.9 (1100)	
Apparent Opening Size (AOS) ²	ASTM D 4751	mm (U.S. Sieve)	0.43 (40)	
Permittivity	ASTM D 4491	sec ⁻¹	0.16	
Flow Rate	ASTM D 4491	l/min/m ² (gal/min/ft ²)	407 (10)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

¹ ASTM D 4833 has been replaced with ASTM D 6241

² ASTM D 4751, AOS is a Maximum Opening Diameter Value

Physical Properties	Test Method	Unit	Typical Value	
Weight	ASTM D 5261	g/m ² (oz/yd ²)	169 (5.0)	
Thickness	ASTM D 5199	mm (mils)	0.5 (20)	
Roll Dimensions (width x length)	--	m (ft)	3.8 x 110 (12.5 x 360)	5.3 x 78.7 (17.5 x 258)
Roll Area	--	m ² (yd ²)	418 (500)	418 (500)
Estimated Roll Weight	--	kg (lb)	102 (225)	102 (225)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.